



TU-872 SLK Sp

Core: TU-872 SLK Sp

Prepreg: TU-87P SLK Sp

TU-872 SLK Sp is based on a high performance modified epoxy FR-4 resin. This material is reinforced with novel woven glass and designed with extra low dielectric constant and low dissipation factor for high speed low loss and high frequency circuit board application. TU-872 SLK Sp material is suitable for environmental protection lead free process and also compatible with FR-4 processes. TU-872 SLK Sp laminates also exhibit excellent CTE, superior chemical resistance, moisture resistance, thermal stability, CAF resistance and toughness enhanced by an allyl network forming compound.

Applications

- Radio Frequency
- Backpanel, High performance computing
- Line cards, Storage
- Servers, Telecom, Base station
- Office Routers

Performance and Processing Advantages

- Excellent electrical properties
- Dielectric constant less than 3.5
- Dissipation factor less than 0.010
- Excellent, stable and flat Dk/Df performance
- Compatible with most FR-4 processes
- Lead free process compatible
- Improved z-axis thermal expansion
- Anti-CAF capability
- Superior dimensional stability, thickness uniformity and flatness
- Excellent through-hole and soldering reliability

Industry Approvals

- IPC-4101E Type Designation : /29, /99, /101, /126
- IPC-4101E/126 Validation Services QPL Certified
- UL Designation – ANSI Grade: FR-4.0
- UL File Number: E189572
- Flammability Rating: 94V-0
- Maximum Operating Temperature: 130°C

Standard Availability

- Thickness: 0.002" [0.05mm] to 0.062" [1.58mm], available in sheet or panel form
- Copper Foil Cladding: 1/3 to 5 oz for built-up & double sides
- Prepregs: Available in roll or panel form
- Glass Styles: 106, 1080 and 2116



Typical Properties for TU-872 SLK Sp Laminate			
	Typical Values	Conditioning	IPC-4101 /126
Thermal			
Tg (DMA)	220°C	E-2/105	> 170°C
Tg (DSC)	200°C		
Tg (TMA)	190°C		
Td (TGA)	340°C		
CTE x-axis	12~15 ppm/°C	E-2/105	N/A
CTE y-axis	12~15 ppm/°C		N/A
CTE z-axis	2.3 %		< 3.0%
Thermal Stress, Solder Float, 288°C	> 60 sec	A	> 10 sec
T260	60 min	E-2/105	> 30 min
T288	20 min		> 15 min
T300	5 min		> 2 min
Flammability	94V-0	E-24/125	94V-0
Electrical			
Permittivity (RC50%)		E-2/105	< 5.2
1GHz (SPC method/4291B)	3.6/3.4		
5GHz (SPC method)	3.5		
10GHz (SPC method)	3.5		
Loss Tangent (RC50%)		E-2/105	< 0.035
1GHz (SPC method/4291B)	0.006/0.004		
5GHz (SPC method)	0.007		
10GHz (SPC method)	0.008		
Volume Resistivity	> 10 ¹⁰ MΩ·cm	C-96/35/90	> 10 ⁶ MΩ·cm
Surface Resistivity	> 10 ⁸ MΩ	C-96/35/90	> 10 ⁴ MΩ
Electric Strength	> 40 KV/mm	A	> 30 KV/mm
Dielectric Breakdown	> 50 kV	A	N/A
Mechanical			
Young's Modulus		A	N/A
Warp Direction	26 GPa		
Fill Direction	24 GPa		
Flexural Strength		A	> 60,000 psi
Lengthwise	> 60,000 psi		
Crosswise	> 50,000 psi	A	> 50,000 psi
Peel Strength, 1.0 oz RTF Cu foil	4~7 lb/in	A	> 4 lb/in
Water Absorption	0.13 %	E-1/105+D-24/23	< 0.5 %

NOTE:

1. Property values are for information purposes only and not intended for specification.
2. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.
3. This product is based on a patent pending technology.

博锐电路始终坚持“品质至上，服务根本”的原则。为客户提供高效制造及可靠品质，迅速获得最佳的市场和竞争优势，是我们永恒的目标。

如您需要工程技术支持或报价服务，请联系工程技术：eq@brpcb.com；商务报价：sales@brpcb.com Web：www.brpcb.com
陈工10年PCB工程经验，专门为电子工程师提供2-36层（HDI任意阶阻抗）叠层阻抗设计 Tel：19195667992 0755-23599845