



S1130

(UL ANSI: FR-4.0) Conventional FR-4

FEATURES

- Natural color
- DICY cured laminate
- Non-UV Blocking/AOI properties
- Excellent mechanical process ability

APPLICATIONS

Communication equipment,
Computer, VCR, TV,
Instrumentation, Game machine.
Not suitable for Anti-CAF application
Not suitable for >2oz copper, HDI,
and ≥12L application

GENERAL PROPERTIES

Test Items	Test Method	Test Condition	Unit	Typical Value
Tg	IPC-TM-650 2.4.25D	DSC	°C	135
Td	IPC-TM-650 2.4.24.6	TGA (5% W.L)	°C	310
T288	IPC-TM-650 2.4.24.1	TMA	min	1
T260	IPC-TM-650 2.4.24.1	TMA	min	13
Thermal Stress	IPC-TM-650 2.4.13.1	288°C, solder dip	s	>60
CTE (Z-axis)	IPC-TM-650 2.4.24	Before Tg	ppm/°C	65
	IPC-TM-650 2.4.24	After Tg	ppm/°C	310
	IPC-TM-650 2.4.24	50-260°C	%	4.5
Permittivity (1GHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	4.4
Loss Tangent (1GHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	0.013
Volume Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ-cm	4.8×10 ⁸
Surface Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ	5.2×10 ⁷
Arc Resistance	IPC-TM-650 2.5.1	D-48/50+D-0.5/23	s	120
Dielectric Breakdown	IPC-TM-650 2.5.6	D-48/50+D-0.5/23	kV	>60
Peel Strength (1oz)	IPC-TM-650 2.4.8	288°C/10s	N/mm [lb/in]	1.8 [10.28]
Flexural Strength (LW/CW)	IPC-TM-650 2.4.4	A	Mpa	600/500
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.15
Flammability	UL94	C-48/23/50	Rating	V-0
CTI	IEC 60112	A	Rating	PLC 3

Remarks: 1. Specification sheet: IPC-4101/21, is for your reference only.
2. All the typical value is based on the 1.6mm (8*7628) specimen.
3. All the typical value listed above is for your reference only, please turn to Shengyi Technology Co., Ltd for detailed information, and all rights from this data sheet are reserved by Shengyi Technology Co., Ltd.

博锐电路始终坚持“品质至上，服务根本”，的原则。为客户提供高效制造及可靠品质，迅速获得最佳的市场和竞争优势，是我们永恒的目标。
如您需工程技术支持或报价服务，请联系工程技术：eq@brpcb.com；商务报价：sales@brpcb.com Web：www.brpcb.com
陈工10年PCB工程经验，专门为电子工程师提供2-36层（HDI任意阶阻抗）叠层阻抗设计服务 Tel：19195667992 0755-23599845



S0101 PREPREG

(UL ANSI: FR-4.0) Bonding Prepreg For S1130

PREPREG PARAMETERS

Glass fabric type	Resin content (%)	Cured thickness (mm)	Standard size (Roll type)
106/1037	71	0.050	1.260m×150m
	74	0.057	
	76	0.062	
1080/1078	64	0.078	1.260m×300m
	68	0.090	
2313/3313	55	0.100	
2116	50	0.114	1.260m×250m
	52	0.120	
	55	0.129	
	58	0.140	
7628	43	0.195	1.260m×150m
	45	0.205	
	48	0.220	
	50	0.230	

Other type, resin content and size could be available upon request.

HOT PRESSING CYCLE

- The heat-up rate depends on the inner copper or the structure of multilayer PCB.
- Curing time: >30min (170~180℃).
- If you need any more detail information, please turn to Shengyi Technology Co., Ltd.

STORAGE CONDITION

- 3 months when stored at < 23℃ and <50% RH.
- 6 months when stored at <5℃. Normalize in room temperature for at least 4h before using.
- Beware of moisture, always keep wrapped in damp-proof material. Keeping in normal condition, prepreg might absorb moisture and its bonding strength would be weakened.
- Avoid UV-rays and strong light.

PURCHASING INFORMATION

Thickness	Copper foil	Standard size
0.05mm to 3.2mm	12um to 70 um	1,020mm ×1,220mm(40"×48") 915mm ×1,220mm(36"×48")
		1,070mm ×1,220mm(42"×48")

Remarks: Other sheet size and thickness could be available upon request.

博锐电路始终坚持“品质至上，服务根本”，的原则。为客户提供高效制造及可靠品质，迅速获得最佳的市场和竞争优势，是我们永恒的目标。

如您需要工程技术支持或报价服务，请联系工程技术：eq@brpcb.com；商务报价：sales@brpcb.com Web：www.brpcb.com
陈工10年PCB工程经验，专门为电子工程师提供2-36层（HDI任意阶阻抗）叠层阻抗设计服务 Tel：19195667992 0755-23599845
CN-TDS-1810-02-S1130-S0101