



S1600

(UL ANSI: FR-4.0) High CTI

FEATURES

- High CTI
- UV Blocking
- Good mechanical process ability
- Not recommended for solder mask rework

APPLICATIONS

PDP, LCD, TV, Refrigerator
Power supplier, Washing machine
For applications with CAF requirements,
recommend customer to carry a systematic
assessment of its reliability.

GENERAL PROPERTIES

Test Items	Test Method	Test Condition	Unit	Typical Value
Tg	IPC-TM-650 2.4.25D	DSC	°C	135
Td	IPC-TM-650 2.4.24.6	TGA (5% W.L)	°C	310
T288	IPC-TM-650 2.4.24.1	TMA	min	2
T260	IPC-TM-650 2.4.24.1	TMA	min	15
Thermal Stress	IPC-TM-650 2.4.13.1	288°C, solder dip	s	>100
CTE (Z-axis)	IPC-TM-650 2.4.24	Before Tg	ppm/°C	55
	IPC-TM-650 2.4.24	After Tg	ppm/°C	308
	IPC-TM-650 2.4.24	50-260°C	%	4.5
Permittivity (1GHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	4.5
Loss Tangent (1GHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	0.017
Volume Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ-cm	5.0×10 ⁸
Surface Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ	5.0×10 ⁷
Arc Resistance	IPC-TM-650 2.5.1	D-48/50+D-0.5/23	s	126
Dielectric Breakdown	IPC-TM-650 2.5.6	D-48/50+D-0.5/23	kV	>45
Peel Strength (1oz)	IPC-TM-650 2.4.8	288°C/10s	N/mm [lb/in]	1.8 [10.28]
Flexural Strength (LW/CW)	IPC-TM-650 2.4.4	A	MPa	550/450
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.10
Flammability	UL94	C-48/23/50	Rating	V-0
CTI	IEC60112	A	Rating	PLC 0 (≥600V)

Remarks: 1. Specification sheet: IPC-4101/21, is for your reference only.
2. All the typical value is based on the 1.6mm (8*7628) specimen.
3. All the typical value listed above is for your reference only, please turn to Shengyi Technology Co., Ltd for detailed information, and all rights from this data sheet are reserved by Shengyi Technology Co., Ltd.

PURCHASING INFORMATION

Thickness	Copper foil	Standard size
0.8mm to 3.2mm	12um to 70 um	1,020mm ×1,220mm(40"×48") 915mm ×1,220mm (36"×48") 1,070mm ×1,220mm(42"×48")

Remarks: Other sheet size and thickness could be available upon request.

CN-TDS-2101-04-S1600

博锐电路始终坚持"品质至上, 服务根本", 的原则。为客户提供高效制造及可靠品质, 迅速获得最佳的市场和竞争优势, 是我们永恒的目标。

如您需要工程技术支持或报价服务, 请联系工程技术: eq@brpcb.com ; 商务报价: sales@brpcb.com Web: www.brpcb.com
陈工10年PCB工程经验, 专门为电子工程师提供2-36层 (HDI任意阶阻抗) 叠层阻抗设计服务 Tel: 19195667992 0755-23599845